



PVC Windows

404 Roblin Blvd.
Winkler, Mb.
R6W 0N4

Phone: (204) 325-8053
Fax: (204) 325-5516
Web: www.Berdick.com

Product Series	GLAZING OPTIONS					THERMAL PERFORMANCE			
	# of panes of Glass	# of Low E Films	Low-E Type	Glazing Cavity	Grille Bar	Visual Transmittance (VT)	U-Factor (W/m2k)	Window SHGC	Energy Rating (Calculated) (ER)
2445/2550 Series Picture Window	2	1	180 Low-E	Argon		0.7	1.53	0.57	39
2445/2550 Series Picture Window	2	1	180 Low-E	Argon	Y	0.63	1.53	0.52	36
2445/2550 Series Picture Window	2	1	272 Low-E	Argon		0.64	1.48	0.57	29
2445/2550 Series Picture Window	2	1	272 Low-E	Argon	Y	0.57	1.48	0.33	36
2445/2550 Series Picture Window	3	1	180 Low-E	Argon		0.64	1.19	0.52	44
2445/2550 Series Picture Window	3	1	180 Low-E	Argon	Y	0.57	1.25	0.47	40
2445/2550 Series Picture Window	3	1	272 Low-E	Argon		0.58	1.14	0.34	34
2445/2550 Series Picture Window	3	1	272 Low-E	Argon	Y	0.52	1.19	0.31	32
2600 Series Awning Window	2	1	180 Low-E	Argon		0.53	1.53	0.44	32
2600 Series Awning Window	2	1	180 Low-E	Argon	Y	0.48	1.53	0.4	29
2600 Series Awning Window	2	1	272 Low-E	Argon		0.48	1.48	0.28	24
2600 Series Awning Window	2	1	272 Low-E	Argon	Y	0.43	1.48	0.26	22
2600 Series Awning Window	3	1	180 Low-E	Argon		0.48	1.19	0.4	37
2600 Series Awning Window	3	1	180 Low-E	Argon	Y	0.44	1.25	0.36	33
2600 Series Awning Window	3	1	272 Low-E	Argon		0.44	1.19	0.26	29
2600 Series Awning Window	3	1	272 Low-E	Argon	Y	0.4	1.19	0.24	28
2600 Series Casement Window	2	1	180 Low-E	Argon		0.53	1.48	0.44	33
2600 Series Casement Window	2	1	180 Low-E	Argon	Y	0.48	1.48	0.4	30
2600 Series Casement Window	2	1	272 Low-E	Argon		0.48	1.48	0.28	24
2600 Series Casement Window	2	1	272 Low-E	Argon	Y	0.43	1.48	0.26	22
2600 Series Casement Window	3	1	180 Low-E	Argon		0.48	1.19	0.4	37
2600 Series Casement Window	3	1	180 Low-E	Argon	Y	0.44	1.25	0.36	33
2600 Series Casement Window	3	1	272 Low-E	Argon		0.44	1.19	0.26	29
2600 Series Casement Window	3	1	272 Low-E	Argon	Y	0.4	1.19	0.24	28
2630/2640 Series Fixed Window	2	1	180 Low-E	Argon		0.62	1.53	0.51	36
2630/2640 Series Fixed Window	2	1	180 Low-E	Argon	Y	0.55	1.53	0.46	33
2630/2640 Series Fixed Window	2	1	272 Low-E	Argon		0.56	1.48	0.33	26
2630/2640 Series Fixed Window	2	1	272 Low-E	Argon	Y	0.5	1.48	0.3	25
2630/2640 Series Fixed Window	3	1	180 Low-E	Argon		0.57	1.19	0.47	41
2630/2640 Series Fixed Window	3	1	180 Low-E	Argon	Y	0.5	1.25	0.42	37
2630/2640 Series Fixed Window	3	1	272 Low-E	Argon		0.51	1.14	0.3	32
2630/2640 Series Fixed Window	3	1	272 Low-E	Argon	Y	0.46	1.19	0.27	29

*Performance Ratings For 1 Low-E Coat

**Based on 3mm/4mm Glass Thickness

***For 2 Low-E Coatings or 5mm/6mm Glass Ratings, Please contact our office.

Custom is the new normal.